

TECHNICAL DATA SHEET



Mon-Droguiste.Com
39 Bis Rue Du Moulin Rouge
10150 Charmont Sous Barbuise
Tél : +33.(0)3.25.41.04.05
Email : contact@mon-droguiste.com
Web : www.mon-droguiste.com

Huile de Lin Cuite

DESCRIPTION

Boiled oils are pre-oxidized linseed oils with appropriate cocktail of dryers.

STANDARD ANALYSIS

TEST	SPECIFICATION	METHOD
*Appearance	Liquid	OLEOA200
*Acid value, mg KOH/g	Max 5	OLEOA232
*Colour Gardner	Max 10	OLEOA210
*Viscosity 20°C, dPa.s	Min 0,7	OLEOA222
*Drying time, hours	Max 14	OLEOT100

ADDITIONAL INFORMATION

TEST	TYPICAL VALUE	METHOD
Biobased content, %	Min 99,5	OLEOA700
Density 20°C, g/ml	Approx. 0,94	OLEOA330
Saponification value , mg KOH/g	190 - 215	OLEOA305
Solid content, wt. %	100	OLEOA281

PROPERTIES/APPLICATIONS

Good drying and protecting properties, excellent penetration into wood.
Improve the gloss of pigments, accentuate the grain patterns of wood.
Good anti-rust properties.

Raw material used in varnishes, natural paints and stains for wood.
Anti-spalling agent for concrete and stone.
Additive for metal protection.

PACKING

Drums, IBC containers, bulk.

STORAGE

5 - Stored in the original sealed packing at 25°C, the product stays in standard specifications for 24 months. For bulk delivery, the product stored in a closed stainless steel tank (max 25 °C) stays in standard specifications for 1 month taken from date of departure from our plant.

OTHER

Disclaimer: the information contained in this data sheet is the state of our knowledge at the date of revision. The producer will not endorse any responsibility concerning the usage made of the product by the customer.

(*) Tests included in the Certificate of Analysis
OLEO-031/01 - 12/12/2017 - Standard